

## Properties

	<b>Description</b> Full grain, semi-aniline leather Available in 75 in-stock colors	<b>Thickness</b> 1.1mm +/- 0.1mm	<b>Grain Characteristics</b> Natural variations
	<b>Hide Size</b> 55.00 sq. ft. avg.	<b>Weight</b> 2.75oz +/- 0.25oz per sq. ft.	<b>Finish Characteristics</b> Durable

## Test Performance

<b>AATCC Method 16, Option E Light Fastness</b> Class 4-5 (72 hours)	<b>ASTM D-2208 Breaking Force</b> 150 lbs.	<b>ASTM D-4705 Stitch Tear</b> 25 lbs.
<b>ASTM D-2097 Newark Flex</b> 70,000 cycles	<b>ASTM D-2211 Elongation</b> 30%-60% at 50 lbs.	<b>ASTM D-5053 Crock Fastness</b> Class 4-5 (dry rub) Class 4 (wet rub)
	<b>ASTM D-3884 Abrasion Resistance</b> 300+ cycles (H-18) 4,000+ cycles (CS-10)	

## Flame Resistance

<b>California TB 117</b>	<b>ASTM E84 Surface Burning Characteristics</b> Class I*	<b>FAR 25.853 (a) Am. 25-116, App. F, Part I (a)(1)(i)*</b>
<b>Boston Fire Code BFD-IX-1*</b>	<b>FMVSS 302</b>	<b>FAR 25.853 (a) Am. 25-116, App. F, Part I (a)(1)(ii)*</b>
<b>NFPA-260 Cigarette Ignition</b> Class I	<b>IMO A.652 (16) 8.2</b>	<b>FAR 25.853 (c) Am. 25-116, App. F, Part II (a)(4) and (5)*</b>

## Notes

- \*Chatham may be flame treated to meet required flammability regulations.
- Chatham may be used in California TB 133 applications with suitable fire backers.
- Chatham may be considered for all upholstery applications.

### Showrooms

Atlanta  
 Boston  
 Charlotte  
 Chicago  
 Dallas  
 Denver  
 Honolulu  
 Laguna Niguel  
 Los Angeles  
 New York  
 Raleigh  
 San Diego  
 San Francisco

Scottsdale  
 Troy  
 Washington, DC

### International

Australia  
 Belgium  
 Canada  
 Chile  
 Dubai UAE  
 England  
 France  
 Greece  
 Hong Kong  
 New Zealand  
 Portugal  
 Spain  
 Switzerland



1360 Niagara Street  
 Buffalo, New York 14213  
 800.342.7738 / 716.882.9301  
 Fax 716.882.9358

www.garrettleather.com