


Properties

	<p>Description Enhanced grain, semi-aniline leather Available in 50 in-stock colors</p>	<p>Thickness 1.1mm +/- 0.1mm</p>	<p>Grain Characteristics Uniform, visible hair cell</p>
	<p>Hide Size 54.00 sq. ft. avg.</p>	<p>Weight 2.75oz +/- 0.25oz per sq. ft.</p>	<p>Finish Characteristics Durable</p>

Test Performance

<p>AATCC Method 16, Option E Light Fastness Class 4-5 (72 hours)</p>	<p>ASTM D-2208 Breaking Force 150 lbs.</p>	<p>ASTM D-4705 Stitch Tear 25 lbs.</p>
<p>ASTM D-2097 Newark Flex 70,000 cycles</p>	<p>ASTM D-2211 Elongation 30%-50% at 50 lbs.</p>	<p>ASTM D-5053 Crock Fastness Class 4-5 (dry rub) Class 4 (wet rub)</p>
	<p>ASTM D-3884 Abrasion Resistance 300+ cycles (H-18) 4,000+ cycles (CS-10)</p>	

Flame Resistance

<p>California TB 117</p>	<p>ASTM E84 Surface Burning Characteristics Class I</p>	<p>FAR 25.853 (a) Am. 25-116, App. F, Part I (a)(1)(i)</p>
<p>Boston Fire Code BFD-IX-1</p>	<p>FMVSS 302</p>	<p>FAR 25.853 (a) Am. 25-116, App. F, Part I (a)(1)(ii)</p>
<p>NFPA-260 Cigarette Ignition Class I</p>		<p>FAR 25.853 (c) Am. 25-116, App. F, Part II (a)(4) and (5)</p>

Notes

- All Avion colors are flame treated in the drum during the tanning process.
- Avion may be used in California TB 133 applications with suitable fire backers.
- Avion may be considered for all upholstery applications.

Showrooms

Atlanta	New York
Charlotte	Philadelphia
Chicago	Raleigh
Cincinnati	San Diego
Dallas	San Francisco
Honolulu	Scottsdale
Houston	Seattle
Laguna Niguel	Troy
Los Angeles	Washington DC

International

Auckland
Dubai
Greece
Hong Kong
London
Paris
Switzerland
Sydney



1360 Niagara Street
Buffalo, New York 14213
800.342.7738 / 716.882.9301
Fax 716.882.9358

www.garrettleather.com