


## Properties

	<b>Description</b> Enhanced grain, semi-aniline leather Available in 10 in-stock colors	<b>Thickness</b> 1.1mm +/- 0.1mm	<b>Grain Characteristics</b> Smooth
	<b>Hide Size</b> 50.00 sq. ft. avg.	<b>Weight</b> 2.75oz +/- 0.25oz per sq. ft.	<b>Finish Characteristics</b> High gloss

## Test Performance

<b>AATCC Method 16, Option E Light Fastness</b> Class 4-5 (72 hours)	<b>ASTM D-2208 Breaking Force</b> 150 lbs.	<b>ASTM D-4705 Stitch Tear</b> 25 lbs.
<b>ASTM D-2097 Newark Flex</b> 70,000 cycles	<b>ASTM D-2211 Elongation</b> 30%-60% at 50 lbs.	<b>ASTM D-5053 Crock Fastness</b> Class 4-5 (dry rub) Class 4 (wet rub)
	<b>ASTM D-3884 Abrasion Resistance</b> 1,000+ cycles (CS-10)	

## Flame Resistance

California TB 117  Boston Fire Code BFD-IX-1*  NFPA-260 Cigarette Ignition Class I	<b>ASTM E84 Surface Burning Characteristics</b> Class I*  <b>FMVSS 302</b>	<b>FAR 25.853 (a) Am. 25-116, App. F, Part I (a)(1)(i)*</b>  <b>FAR 25.853 (a) Am. 25-116, App. F, Part I (a)(1)(ii)*</b>  <b>FAR 25.853 (c) Am. 25-116, App. F, Part II (a)(4) and (5)*</b>
---	---	--

## Notes

- \*Glazed may be flame treated to meet required flammability regulations.
- Glazed may be used in California TB 133 applications with suitable fire backers.
- Glazed may be considered for all upholstery applications.

### Showrooms

Atlanta	New York
Charlotte	Philadelphia
Chicago	Raleigh
Cincinnati	San Diego
Dallas	San Francisco
Honolulu	Scottsdale
Houston	Seattle
Laguna Niguel	Troy
Los Angeles	Washington DC

### International

Auckland  
Dubai  
Greece  
Hong Kong  
London  
Paris  
Switzerland  
Sydney



1360 Niagara Street  
Buffalo, New York 14213  
800.342.7738 / 716.882.9301  
Fax 716.882.9358

www.garrettleather.com